



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with low water absorption $E_v \leq 0,5\%$ Group BIa

Californian Wood

Line Ecodiversa

Tipology

Glazed Porcelain Tile

Code

27687E

Size (cm)

15X60

Thickness (mm)

8.50

Work Size (cm)

148,0X605,0

Edge

Bold

Surface

Natural

Tonality Variation

V3

Physical Property

| |
|---|
| Water Absorption (%) |
| Modulus of Breaking Strength (N/mm ²) |
| Breaking Load (N) |
| Moisture Expansion (mm/m) |
| Crazing Resistance |
| Frost Resistance |
| Resistance to Thermal Shock |

Test Standards

| |
|--------------|
| ISO 10545-3 |
| ISO 10545-4 |
| ISO 10545-4 |
| ISO 10545-10 |
| ISO 10545-11 |
| ISO 10545-12 |
| ISO 10545-9 |

Results

| |
|--------|
| 0,5 |
| 35 |
| 1300 |
| 0,1 |
| RESIST |
| RESIST |
| RESIST |

Chemical Property

Resistance to Staining

| |
|--------------|
| Glazed Tiles |
|--------------|

Test Standards

| |
|--------------|
| ISO 10545-14 |
|--------------|

Results

| |
|---|
| 5 |
|---|

Resistance to Chemicals

| |
|---|
| Resistance to low concentrations of acids and alkalis |
| Resistance to household chemicals and swimming pool salts |

| |
|--------------|
| ISO 10545-13 |
| ISO 10545-13 |

| |
|----|
| LB |
| B |

Coefficient of Friction

| |
|-------------|
| Dry Surface |
| Wet Surface |
| Wet Surface |

Test Standards

| |
|----------------|
| ABNT NBR 16919 |
| ABNT NBR 16919 |
| ANSI A326.3 |

Results

| |
|------|
| 0,5 |
| 0,4 |
| 0,43 |

Local of Use

CI - Commercial Light | RE - Residential | FA - Facade

Settlement

Recomendado

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000

