



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with low water absorption
0,5% < Ev ≤ 3,0% Group BIb

Trace Linen Mix

Line Stone Lab

Tipology	Code	
	212232E	
Size (cm)	Thickness (mm)	Work Size (cm)
09X37	8.00	9,18X37,2
Edge	Surface	Tonality Variation
Bold	Natural	V2

Physical Property

Water Absorption (%)
Modulus of Breaking Strength (N/mm²)
Breaking Load (N)
Moisture Expansion (mm/m)
Crazing Resistance
Frost Resistance
Resistance to Thermal Shock

Test Standards

ISO 10545-3
ISO 10545-4
ISO 10545-4
ISO 10545-10
ISO 10545-11
ISO 10545-12
ISO 10545-9

Results

3
38
1100
0,1
RESIST
RESIST
RESIST

Chemical Property

Resistance to Staining

Glazed Tiles

Test Standards

ISO 10545-14

Results

3

Resistance to Chemicals

Resistance to low concentrations of acids and alkalis
Resistance to household chemicals and swimming pool salts

ISO 10545-13
ISO 10545-13

LB
A

Local of Use

FA - Facade

Settlement

Dry Internal Walls Joint	2 mm
Wet Internal Walls Joint	2 mm
External Walls Joint - Facade	2 mm
Floor joint	2 mm

Recomendado

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello



Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000