



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with water absorption $3\% < E_v \leq 6\%$ Group BIIa

Buffalo

Line Surfaces

Tipology

Mosaic

Code

203140E

Size (cm)

9,5X9,5

Thickness (mm)

6.50

Work Size (cm)

9,5X9,5

Edge

Surface

Matte

Tonality Variation

V1

Physical Property

Water Absorption (%)	ISO 10545-3	6
Modulus of Breaking Strength (N/mm ²)	ISO 10545-4	22
Breaking Load (N)	ISO 10545-4	600
Moisture Expansion (mm/m)	ISO 10545-10	0,3
Crazing Resistance	ISO 10545-11	RESIST
Frost Resistance	ISO 10545-12	NO RESIST
Resistance to Thermal Shock	ISO 10545-9	RESIST

Test Standards

Results

Chemical Property

Resistance to Staining

Glazed Tiles	ISO 10545-14	5
--------------	--------------	---

Resistance to Chemicals

Resistance to low concentrations of acids and alkalis	ISO 10545-13	LB
Resistance to household chemicals and swimming pool salts	ISO 10545-13	A

Test Standards

Results

Coefficient of Friction

Dry Surface
Wet Surface
Wet Surface

Test Standards

ABNT NBR 16919
ABNT NBR 16919
ANSI A326.3

Results

0,5
0,4
0,43

Dimensions and surface quality

Length and width (mm)
Width (mm)
Thickness (mm)
Straightness of sides (mm)
Rectangularity (mm)
Surface flatness (mm)
Surface quality (%)

Test Standards

ISO 10545-2
ISO 10545-2
ISO 10545-2
ISO 10545-2
ISO 10545-2
ISO 10545-2
ISO 10545-2

Results

± 0,90
± 0,90
± 0,50
± 0,80
± 0,80
± 0,8 mm
≥ 95

Local of Use

RE - Residential FA - Facade

Settlement

Dry Internal Walls Joint
Wet Internal Walls Joint
External Walls Joint - Facade
Floor joint

Recomendado

3 mm
3 mm
3 mm
3 mm

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000

