


Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with water absorption 3% < Ev ≤ 6% Group BIIa

Rouge

Line Surfaces

Tipology **Mosaic**	Code **203248E**	
Size (cm) **7,5X7,5**	Thickness (mm) **6.8**	Work Size (cm) **7,3X7,3**
Edge	Surface **Matte**	Tonality Variation **V1**

Physical Property	Test Standards	Results
Water Absorption (%)	ISO 10545-3	6
Modulus of Breaking Strength (N/mm²)	ISO 10545-4	22
Breaking Load (N)	ISO 10545-4	600
Moisture Expansion (mm/m)	ISO 10545-10	0,3
Crazing Resistance	ISO 10545-11	RESIST
Frost Resistance	ISO 10545-12	NO RESIST
Resistance to Thermal Shock	ISO 10545-9	RESIST

Chemical Property	Test Standards	Results
Resistance to Staining		
Glazed Tiles	ISO 10545-14	5
Resistance to Chemicals		
Resistance to low concentrations of acids and alkalis	ISO 10545-13	LB
Resistance to household chemicals and swimming pool salts	ISO 10545-13	A

Para informações de recomendações de aplicação consulte o especificador virtual: http://especificadorvirtual.portobello.com.br
Tijucas, 12/11/2026

Coefficient of Friction	Test Standards	Results
Dry Surface	ABNT NBR 16919	0,5
Wet Surface	ABNT NBR 16919	0,4
Wet Surface	ANSI A326.3	0,43

Dimensions and surface quality	Test Standards	Results
Length and width (mm)	ISO 10545-2	± 0,90
Width (mm)	ISO 10545-2	± 0,90
Thickness (mm)	ISO 10545-2	± 0,50
Straightness of sides (mm)	ISO 10545-2	± 0,80
Rectangularity (mm)	ISO 10545-2	± 0,80
Surface flatness (mm)	ISO 10545-2	± 0,8 mm
Surface quality (%)	ISO 10545-2	≥ 95

Local of Use

RE - Residential | FA - Facade

Settlement	Recomendado
Dry Internal Walls Joint	3 mm
Wet Internal Walls Joint	3 mm
External Walls Joint - Facade	3 mm
Floor joint	3 mm

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000