



# Technical Specifications

## ABNT NBR ISO 13006

Dry-pressed ceramic tiles with water absorption  $3\% < E_v \leq 6\%$  Group BIIa

## Truffle

Line Surfaces

Tipology

**Mosaic**

Code

**203237E**

Size (cm)

**7,5X7,5**

Thickness (mm)

**6.8**

Work Size (cm)

**7,3X7,3**

Edge

Surface

**Matte**

Tonality Variation

**V1**

### Physical Property

Water Absorption (%)
Modulus of Breaking Strength (N/mm <sup>2</sup> )
Breaking Load (N)
Moisture Expansion (mm/m)
Crazing Resistance
Frost Resistance
Resistance to Thermal Shock

### Test Standards

ISO 10545-3
ISO 10545-4
ISO 10545-4
ISO 10545-10
ISO 10545-11
ISO 10545-12
ISO 10545-9

### Results

6
22
600
0,3
RESIST
NO RESIST
RESIST

### Chemical Property

#### Resistance to Staining

Glazed Tiles
--------------

### Test Standards

ISO 10545-14
--------------

### Results

5
---

#### Resistance to Chemicals

Resistance to low concentrations of acids and alkalis
Resistance to household chemicals and swimming pool salts

ISO 10545-13
ISO 10545-13

LB
A

## Coefficient of Friction

Dry Surface	ABNT NBR 16919	0,5
Wet Surface	ABNT NBR 16919	0,4
Wet Surface	ANSI A326.3	0,43

## Dimensions and surface quality

	Test Standards	Results
Length and width (mm)	ISO 10545-2	± 0,90
Width (mm)	ISO 10545-2	± 0,90
Thickness (mm)	ISO 10545-2	± 0,50
Straightness of sides (mm)	ISO 10545-2	± 0,80
Rectangularity (mm)	ISO 10545-2	± 0,80
Surface flatness (mm)	ISO 10545-2	± 0,8 mm
Surface quality (%)	ISO 10545-2	≥ 95

## Local of Use

RE - Residential   FA - Facade
--------------------------------

## Settlement

	Recomendado
Dry Internal Walls Joint	3 mm
Wet Internal Walls Joint	3 mm
External Walls Joint - Facade	3 mm
Floor joint	3 mm

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

# Portobello

Portobello SA - Fábrica | contato@portobello.com.br  
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15  
Tijucas/SC - Brasil - 88200-000

