



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with low water absorption $E_v \leq 0,5\%$ Group Bla

Araxa

Line Quartzites

Tipology

**Glazed
Porcelain Tile**

Code

12150E

Format (cm)

120X270

Thickness (mm)

7,00

Work Size (cm)

119,85X269,85

Edge

Rectified

Surface

Polished

Physical Property

Water Absorption (%)
Modulus of Breaking Strength (N/mm ²)
Breaking Load (N)
Moisture Expansion (mm/m)
Crazing Resistance
Frost Resistance
Resistance to Thermal Shock

Test Standards

ISO 10545-3
ISO 10545-4
ISO 10545-4
ISO 10545-10
ISO 10545-11
ISO 10545-12
ISO 10545-9

Results

0,5
40
1500
0,1
Resist
Resist
Resist

Chemical Property

Resistance to Staining

Glazed Tiles

Test Standards

ISO 10545-14

Results

3

Resistance to Chemicals

Resistance to low concentrations of acids and alkalis
Resistance to household chemicals and swimming pool salts

ISO 10545-13
ISO 10545-13

LB
A

Coefficient of Friction	Test Standards	Results
Dry Surface	ABNT NBR 16919	0,3
Wet Surface	ABNT NBR 16919	0,3
Wet Surface	ANSI A326.3	0,3

Local of Use

CI - Commercial Light RE - Residential FA - Facade
--

Settlement	Recomendado
Dry Internal Walls Joint	1,5 mm
Wet Internal Walls Joint	1,5 mm
External Walls Joint - Facade	1,5 mm
Floor joint	1,5 mm

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000

