




Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with water absorption $E_v > 10\%$ Group BIII

Gouache Mer

Line Gouache

Tipology	Code	
Wall	12854E	
Format (cm)	Thickness (mm)	Work Size (cm)
15,5X15,5	9,00	15,55X15,55
Edge	Surface	
Bold	Glossy	

Physical Property

Water Absorption (%)	ISO 10545-3	13
Modulus of Breaking Strength (N/mm ²)	ISO 10545-4	15
Breaking Load (N)	ISO 10545-4	600
Moisture Expansion (mm/m)	ISO 10545-10	0,3
Crazing Resistance	ISO 10545-11	Resist
Frost Resistance	ISO 10545-12	Not Resist
Resistance to Thermal Shock	ISO 10545-9	Not Resist

Test Standards

Results

Chemical Property

Resistance to Staining

Glazed Tiles	ISO 10545-14	5
--------------	--------------	---

Resistance to Chemicals

Resistance to low concentrations of acids and alkalis	ISO 10545-13	LA
Resistance to household chemicals and swimming pool salts	ISO 10545-13	A

Test Standards

Results

Local of Use

IC - Internal Coating

Settlement

Dry Internal Walls Joint
Wet Internal Walls Joint

Recomendado

1,5 mm
1,5 mm

For the use of this coating on external walls up to 6 meters high, follow the following guidelines:

- Use ACIII adhesive mortar indicated for facade use and compatible with the product's shape, in buildings up to 2 floors. Check with the salesperson for the most suitable mortar. Respect the existing movement and desolidation joints in the architectural design.
- On external walls that do not have coverage and side protection, it is mandatory to protect the top and side of the wall with a drip edge or flashing.
- The seating joints must be used according to the specific indication of each product.
- The grout used to seal the seating joints must be specific for facades.

ATTENTION: Single-porous facades are not recommended for regions with negative temperatures for prolonged periods, such as in Europe and the United States, as established in ISO 13006 for external walls.

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000

