



# Technical Specifications

## ABNT NBR ISO 13006

Dry-pressed ceramic tiles with low water absorption  $E_v \leq 0,5\%$  Group BIa

## Ardos Grey st

Line Ardos

Tipology

**Glazed  
Porcelain Tile**

Code

**212838E**

Size (cm)

**120X120**

Thickness (mm)

**7.00**

Work Size (cm)

**119,85X119,85**

Edge

**Rectified**

Surface

**External**

Tonality Variation

**V4**

### Physical Property

|                                                   |
|---------------------------------------------------|
| Water Absorption (%)                              |
| Modulus of Breaking Strength (N/mm <sup>2</sup> ) |
| Breaking Load (N)                                 |
| Moisture Expansion (mm/m)                         |
| Crazing Resistance                                |
| Frost Resistance                                  |
| Resistance to Thermal Shock                       |

### Test Standards

|              |
|--------------|
| ISO 10545-3  |
| ISO 10545-4  |
| ISO 10545-4  |
| ISO 10545-10 |
| ISO 10545-11 |
| ISO 10545-12 |
| ISO 10545-9  |

### Results

|        |
|--------|
| 0,5    |
| 40     |
| 1300   |
| 0,1    |
| RESIST |
| RESIST |
| RESIST |

### Chemical Property

#### Resistance to Staining

|              |
|--------------|
| Glazed Tiles |
|--------------|

### Test Standards

|              |
|--------------|
| ISO 10545-14 |
|--------------|

### Results

|   |
|---|
| 5 |
|---|

#### Resistance to Chemicals

|                                                           |
|-----------------------------------------------------------|
| Resistance to low concentrations of acids and alkalis     |
| Resistance to household chemicals and swimming pool salts |

|              |
|--------------|
| ISO 10545-13 |
| ISO 10545-13 |

|    |
|----|
| LA |
| A  |

### Coefficient of Friction

|             |
|-------------|
| Dry Surface |
| Wet Surface |
| Wet Surface |

### Test Standards

|                |
|----------------|
| ABNT NBR 16919 |
| ABNT NBR 16919 |
| ANSI A326.3    |

### Results

|     |
|-----|
| 0,7 |
| 0,6 |
| 0,6 |

### Dimensions and surface quality

|                            |
|----------------------------|
| Length and width (mm)      |
| Width (mm)                 |
| Thickness (mm)             |
| Straightness of sides (mm) |
| Rectangularity (mm)        |
| Surface quality (%)        |

### Test Standards

|             |
|-------------|
| ISO 10545-2 |
| ISO 10545-2 |
| ISO 10545-2 |
| ISO 10545-2 |
| ISO 10545-2 |
| ISO 10545-2 |

### Results

|        |
|--------|
| ± 1,00 |
| ± 1,00 |
| ± 0,35 |
| ± 0,80 |
| ± 1,50 |
| ≥ 95   |

### Local of Use

|                                                        |
|--------------------------------------------------------|
| CI - Commercial Light   RE - Residential   FA - Facade |
|--------------------------------------------------------|

### Settlement

|                               |
|-------------------------------|
| Dry Internal Walls Joint      |
| Wet Internal Walls Joint      |
| External Walls Joint - Facade |
| Floor joint                   |

### Recomendado

|        |
|--------|
| 1,5 mm |
| 1,5 mm |
| 1,5 mm |
| 1,5 mm |

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

# Portobello

Portobello SA - Fábrica | contato@portobello.com.br  
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15  
Tijucas/SC - Brasil - 88200-000

