



# Technical Specifications

## ABNT NBR ISO 13006

Dry-pressed ceramic tiles with low water absorption  $E_v \leq 0,5\%$  Group Bla

## Travertino Navona Grigio

Line Travertini

|                              |                |                    |
|------------------------------|----------------|--------------------|
| Tipology                     | Code           |                    |
| <b>Glazed Porcelain Tile</b> | <b>29525E</b>  |                    |
| Format (cm)                  | Thickness (mm) | Work Size (cm)     |
| <b>90X90</b>                 | <b>9,00</b>    | <b>89,85X89,85</b> |
| Edge                         | Surface        |                    |
| <b>Rectified</b>             | <b>Natural</b> |                    |

### Physical Property

|                                      |
|--------------------------------------|
| Water Absorption (%)                 |
| Modulus of Breaking Strength (N/mm²) |
| Breaking Load (N)                    |
| Moisture Expansion (mm/m)            |
| Crazing Resistance                   |
| Frost Resistance                     |
| Resistance to Thermal Shock          |

### Test Standards

|              |
|--------------|
| ISO 10545-3  |
| ISO 10545-4  |
| ISO 10545-4  |
| ISO 10545-10 |
| ISO 10545-11 |
| ISO 10545-12 |
| ISO 10545-9  |

### Results

|        |
|--------|
| 0,5    |
| 37     |
| 1800   |
| 0,1    |
| Resist |
| Resist |
| Resist |

### Chemical Property

#### Resistance to Staining

|              |
|--------------|
| Glazed Tiles |
|--------------|

### Test Standards

|              |
|--------------|
| ISO 10545-14 |
|--------------|

### Results

|   |
|---|
| 5 |
|---|

#### Resistance to Chemicals

|                                                           |
|-----------------------------------------------------------|
| Resistance to low concentrations of acids and alkalis     |
| Resistance to household chemicals and swimming pool salts |

|              |
|--------------|
| ISO 10545-13 |
| ISO 10545-13 |

|    |
|----|
| LA |
| A  |

| Coefficient of Friction | Test Standards | Results |
|-------------------------|----------------|---------|
| Dry Surface             | ABNT NBR 16919 | 0,5     |
| Dry Surface             | ANSI A326.3    | 0,5     |
| Wet Surface             | ABNT NBR 16919 | 0,4     |
| Wet Surface             | ANSI A326.3    | 0,43    |

Local of Use

HC - Heavy Commercial | RE - Residential | FA - Facade

Settlement

|                               |
|-------------------------------|
| Dry Internal Walls Joint      |
| Wet Internal Walls Joint      |
| External Walls Joint - Facade |
| Floor joint                   |

Recomendado

|        |
|--------|
| 1,5 mm |
| 1,5 mm |
| 1,5 mm |
| 1,5 mm |

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br  
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15  
Tijucas/SC - Brasil - 88200-000

