



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with water absorption $E_v > 10\%$ Group BIII

Parquet D'olivier Clapboard

Line Parquet

Tipology	Code	
Wall	201722E	
Format (cm)	Thickness (mm)	Work Size (cm)
30X90	13,3	29,85X89,85
Edge	Surface	
Rectified	Matte	

Physical Property

Water Absorption (%)	ISO 10545-3	17
Modulus of Breaking Strength (N/mm ²)	ISO 10545-4	15
Breaking Load (N)	ISO 10545-4	600
Moisture Expansion (mm/m)	ISO 10545-10	0,3
Crazing Resistance	ISO 10545-11	Resist
Frost Resistance	ISO 10545-12	Not Resist
Resistance to Thermal Shock	ISO 10545-9	Not Resist

Test Standards

Results

Chemical Property

Resistance to Staining

Glazed Tiles	ISO 10545-14	5
--------------	--------------	---

Resistance to Chemicals

Resistance to low concentrations of acids and alkalis	ISO 10545-13	LA
Resistance to household chemicals and swimming pool salts	ISO 10545-13	A

Test Standards

Results

Local of Use

EW - External Wall

Settlement

Dry Internal Walls Joint
Wet Internal Walls Joint

Recomendado

1 mm
1 mm

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000

