



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with low water absorption $E_v \leq 0,5\%$ Group Bla

Superquadra Cru

Line Superquadra

Tipology	Code	
Glazed Porcelain Tile	205849E	
Format (cm)	Thickness (mm)	Work Size (cm)
120X120	7,00	119,85X119,85
Edge	Surface	
Rectified	External	

Physical Property

Water Absorption (%)	ISO 10545-3	0,5
Modulus of Breaking Strength (N/mm ²)	ISO 10545-4	40
Breaking Load (N)	ISO 10545-4	1500
Moisture Expansion (mm/m)	ISO 10545-10	0,1
Crazing Resistance	ISO 10545-11	Resist
Frost Resistance	ISO 10545-12	Resist
Resistance to Thermal Shock	ISO 10545-9	Resist

Test Standards

Results

Chemical Property

Resistance to Chemicals

Resistance to low concentrations of acids and alkalis	ISO 10545-13	LA
---	--------------	----

Test Standards

Results

Coefficient of Friction

Dry Surface	ABNT NBR 16919	0,7
Wet Surface	ABNT NBR 16919	0,6
Wet Surface	ANSI A326.3	0,6

Test Standards

Results

Local of Use

HC - Heavy Commercial | RE - Residential | FA - Facade

Settlement

Dry Internal Walls Joint
Wet Internal Walls Joint
External Walls Joint - Facade
Floor joint

Recomendado

1,5 mm
1,5 mm
1,5 mm
1,5 mm

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello

Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000

