



Technical Specifications

ABNT NBR ISO 13006

Dry-pressed ceramic tiles with water absorption $3\% < E_v \leq 6\%$ Group BIIa

Coal

Line Surfaces

Tipology

Mosaic

Code

203243E

Size (cm)

7,5X7,5

Thickness (mm)

6.8

Work Size (cm)

7,3X7,3

Edge

Surface

Matte

Tonality Variation

V1

Physical Property

| Physical Property | Test Standards | Results |
|---|----------------|---------|
| Water Absorption (%) | ISO 10545-3 | 6 |
| Modulus of Breaking Strength (N/mm ²) | ISO 10545-4 | 22 |
| Breaking Load (N) | ISO 10545-4 | 600 |
| Moisture Expansion (mm/m) | ISO 10545-10 | 0,3 |
| Crazing Resistance | ISO 10545-11 | 0 |
| Frost Resistance | ISO 10545-12 | 0 |
| Resistance to Thermal Shock | ISO 10545-9 | 0 |

Chemical Property

Resistance to Staining

| Chemical Property | Test Standards | Results |
|-------------------|----------------|---------|
| Glazed Tiles | ISO 10545-14 | 5 |

Resistance to Chemicals

| | | |
|---|--------------|----|
| Resistance to low concentrations of acids and alkalis | ISO 10545-13 | LB |
| Resistance to household chemicals and swimming pool salts | ISO 10545-13 | A |

Coefficient of Friction

Test Standards

Results

| | | |
|-------------|----------------|------|
| Dry Surface | ABNT NBR 16919 | 0,5 |
| Wet Surface | ABNT NBR 16919 | 0,4 |
| Wet Surface | ANSI A326.3 | 0,43 |

Local of Use

RE - Residential | FA - Facade

Settlement

Recomendado

| | |
|-------------------------------|------|
| Dry Internal Walls Joint | 3 mm |
| Wet Internal Walls Joint | 3 mm |
| External Walls Joint - Facade | 3 mm |
| Floor joint | 3 mm |

Reaction with fire: Ceramic coatings are sintered at high temperatures and therefore do not present in their final composition organic or volatile compounds of any nature, classifying them as Class I - non-combustible.

Portobello



Portobello SA - Fábrica | contato@portobello.com.br
SAC: 800 648 2002 1 BR 101 - Km 163 - Cx. Postal 15
Tijucas/SC - Brasil - 88200-000